

# Dulux

## **ALKALI RESISTANT PRIMER**

# **PRODUCT USES**

Primes all types of masonry surfaces such as gypsum plaster, brick, concrete, cement, and all types of composition boarding.

# **FEATURES AND BENEFITS**

Versatile high solids plaster primer.

Pigmented white - time saving when top coating.

Combines good alkali resistance with excellent sealing properties.

Serves as a sealer and primer.

Quick drying.

# PRODUCT INFORMATION

Colour White

Density at 23°C Approx.: 1.18 kg/L **Solids Content** By weight: Approx. 57%

By volume : Approx. 34%

Packaged Viscosity Viscosity at 23°C: Approx 75 KU

Approx 9m<sup>2</sup> per litre depending on surface **Spreading Rate** 

Min. 25µm. Max. 35µm.

porosity, profile and application method

Recommended

**DFT** per coat

## APPLICATION INFORMATION

**Application** Surface Temperature between 10 - 35°C conditions Relative Humidity between 10 - 85 %.

Application methods

**Drying Time** 

Brush, roller or spray application

Thinner

Thinning not recommended

Ready for use after thorough stirring

Touch dry 4 hours

(Drying times will be extended during cold,

wet or humid conditions)

**Recoating Time** 

Cleaning of equipment

For clean up use Fixit Brush Cleaner/ **Degreaser** or Mineral Turpentine

Substrates Suitable for cement plaster, gypsum plaster, concrete, fibre cement and all

composition boarding

Primer for new dry interior and exterior porous surfaces











# APPLICATION INFORMATION

## **PRECAUTIONS**

Ensure that surfaces are sound and free from dust, dirt, grease and oil. Surfaces must be thoroughly dry - no more than 12% moisture content.

Do not apply during cold (below 10°C) or wet weather.

Not suitable as a primer for metal surfaces.

Not suitable for direct application to powdery or friable surfaces whether previously painted or not.

Not designed to withstand natural weathering. It should be over coated within 48 hours.

#### TOP COATING

Can be over coated with most Dulux decorative finishes.

## SURFACE PREPARATION

## **NEW SURFACES**

Cement Plaster (non friable), Gypsum Plaster, Composition Boarding, Fibre Cement

It is recommended that fresh plaster should be allowed one week drying for every 5mm thickness; and longer in cold or damp weather.

#### Concrete

Remove any uncured cement, grease, and mouldrelease agents by high-pressure water blast, or wash with a strong solution of sugar soap. Rinse off thoroughly with clean water.

## PREVIOUSLY PAINTED SURFACES

### **Old Paint in Poor Condition**

Strip loose and flaking paint completely and spot prime bare areas.

Friable and porous surfaces must be removed and repaired.

Mould instructions. To kill lichen and algae growth, scrub with one of the following solutions: either 4:1 water/HTH (chlorine), or 4:1 water/JIK (sodium hypochlorite). Ensure that the areas are completely saturated, and allow the solution to react for a minimum of 4 hours. Rinse the complete wall surface thoroughly with clean water.

## Filling

Fill and repair imperfections with the appropriate Fixit filler and prime with **Dulux Trade Alkali Resistant**Plaster Primer once the crack filler has dried properly. Failure to do this will result in uneven sheen levels between the repaired and normal areas.

# HEALTH AND SAFETY INFORMATION

For detailed safety information refer to Material Safety Data Sheet.

Keep out of reach of children.

Ensure good ventilation during application and drying.

Flash Point 37°C.

## **i** ADDITIONAL INFORMATION

#### **Storage Conditions**

Store under cool dry conditions.