

## STEEL PRIMER



### PRODUCT USES

Gives an excellent primed surface for top coating with most decorative Undercoats and Enamels.



### FEATURES AND BENEFITS

High quality general-purpose corrosion resistant metal primer.  
Suitable for new or hand cleaned rusty surfaces.  
Easy brushing and good levelling properties.



### PRODUCT INFORMATION

<b>Colour</b>	Light Grey
<b>Density at 23°C</b>	Approx. : 1.15 kg/L
<b>Solids Content</b>	By weight : Approx. 58% By volume : Approx. 39%
<b>Packaged Viscosity</b>	Viscosity at 23°C : Approx 65 KU
<b>Spreading Rate</b>	Approx 12m <sup>2</sup> per litre depending on surface porosity, profile and application method
<b>Recommended DFT per coat</b>	Min. 25µm. Max. 35µm.



### APPLICATION INFORMATION

<b>Application conditions</b>	Surface Temperature between 10 - 35°C Relative Humidity between 10 - 85 %
<b>Application methods</b>	Brush or roller Brush application preferred to ensure wetting of the surface
<b>Thinner</b>	Thinning not recommended Ready for use after thorough stirring
<b>Drying Time</b>	Touch dry 4 hours (Drying times will be extended during cold, wet or humid conditions)
<b>Recoating Time</b>	18 hours
<b>Cleaning of equipment</b>	For clean up use <b>Fixit Brush Cleaner / Degreaser</b> or Mineral Turpentine.
<b>Substrates</b>	Suitable for iron and steel surfaces

Versatile primer for use on new or lightly rusted iron and steel





## APPLICATION INFORMATION

### PRECAUTIONS

Ensure that surfaces are sound and free from dust, dirt, grease and oil. Surfaces must be thoroughly dry.

Do not apply during cold (below 10°C) or wet weather.

Not designed to withstand natural weathering. It should be over coated within 1 week particularly in a marine atmosphere.

Not suitable for direct application to powdery or friable surfaces whether previously painted or not.

### TOP COATING

Over-coat primer with one overall coat **Dulux Trade Universal Undercoat**, and finish with two top coats **Enamel**.



## SURFACE PREPARATION

### NEW SURFACES

Inspect shop-primer thoroughly for damage by installation. All rust, scale and dirt must be removed by scraping or with steel wire brushes, and then sanded with medium grit sandpaper, finishing with fine grit sandpaper - down to a bright metal finish. Ensure that the sanded areas are dry and free of grease and dust. A solvent wash (rags dipped in lacquer thinner) may be used. Change the rags frequently. Allow drying.

Apply one or two coats **Dulux Trade Steel Primer**, depending on the severity of the conditions. Two Coats are preferred for coastal conditions and chemical works.

### PREVIOUSLY PAINTED SURFACES

Sand enamel surfaces to provide a key and improve adhesion.

Loose, flaking paint must be completely removed prior to spot-priming bare, exposed steel with **Dulux Trade Steel Primer**. Build up spot-primed areas with **Dulux Trade Universal Undercoat** to the same level as the rest of the paintwork.



## HEALTH AND SAFETY INFORMATION

For detailed safety information refer to Material Safety Data Sheet.

Keep out of reach of children.

Ensure good ventilation during application and drying.

Flash Point 37°C.



## ADDITIONAL INFORMATION

### Storage Conditions

Store under cool dry conditions.