

1K Multi Plastic Primer







Primer

24/10/2019

L2.01.05

DESCRIPTION

1K Multi Plastic Primer is an air drying, one-pack primer to promote the adhesion on plastic car-body parts.

Mixing ratio		RFU	1K Multi Plastic Primer
Equipment		Spray gun set-up: 1.3-1.5 mm	Application pressure: 1.7-2.2 bar at the air inlet HVLP max 0.7 bar at the air cap
Application		x 1 coat	
Flash-off		Between coats NA	Recoat after: 20 minutes at 20°C
Application		All Lesonal Primers, Fillers and topcoats	
Protection		Use suitable respiratory protection Akzo Nobel Car Refinishes recommends the use of fresh air supply respirator	
Read complete TDS for detailed product information			

1K Multi Plastic Primer

Primer

24/10/2019

L2.01.05

DESCRIPTION

1K Multi Plastic Primer is an air drying, one-pack primer to promote the adhesion on plastic car-body parts.

PRODUCT AND ADDITIVES


Product 1K Multi Plastic Primer

Basic raw materials Polyolefine resin


METHOD OF USE

Suitable substrates All plastic car parts with the exception of pure PE (polyethylene).

Mixing None, shake well before use.



Spraying Viscosity 14-16 sec. DIN Cup 4 at 20°C.



Spray gun set-up / application pressure	Spray gun Gravity feed	Fluid tip-set-up 1.3-1.5 mm	Application pressure 1.7-2.2 bar at the spray gun air inlet HVLP max 0.7 bar at the air cap
---	------------------------	-----------------------------	--



1K Multi Plastic Primer

Primer

24/10/2019

L2.01.05

APPLICATION TECHNIQUE

Application process
& blending

Apply even closed coat.
Note: minimum application temperature 15°C
Allow for a flash off time of 20 minutes at 20°C



Film Thickness

By using the recommended application: 1-4 µm per coat

Theoretical Coverage

11.4m²/l unthinned paint at 1 µm (the practical material usage depends on many factors, i.e. shape of the object, roughness of the surface, application method and application circumstances).

Recoatability

All Lesonal primers and topcoats

Cleaning of
equipment

Use Lesonal Multi Thinner 810 (any)

Product storage

Product shelf-life is determined when products are stored unopened at 20°C.
Avoid extreme temperature fluctuation.
Product shelf life data see TDS S9.02.01

AkzoNobel Car Refinishes Australia Pty Ltd

Address: 269 Williamstown Road, Port Melbourne, VICTORIA, 3207.

Tel: +61 3 9644 1711

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. <https://www.lesonal.com.au/>